

## TECHNICAL SPECIFICATIONS

(Typical values)

			GRAMMAGE g/m <sup>2</sup>	
			70	80
TENSIBLE ST.	MD	kN/m	6,1	7
	CD	kN/m	3,6	4,1
TENSIBLE INDEX	MD	Nm/g	87	87
	CD	Nm/g	51	51
STRETCH	MD	%	2,5	2,5
	CD	%	7,3	7,2
T.E.A.	MD	J/m <sup>2</sup>	94	107
	CD	J/m <sup>2</sup>	180	205
T.E.A. INDEX	MD	J/g	1,3	1,3
	CD	J/g	2,6	2,6
AIR RESISTANCE		s	20	20
TEAR INDEX	(MD+CD)/2	mNm <sup>2</sup> /g	11	11,5

**COBB TOP FACE (1min) : 30g/m<sup>2</sup>**

**MOISTURE : 6,7%**

Paper properties	Testing method
. Grammage	ISO-536
. Tensile strength	ISO-1924-3
. Stretch	ISO-1924-3
. T.E.A.	ISO-1924-3
. Air Resistance	ISO 5635-5
. Tear Index	ISO 1974-1990
. Cobb	ISO 535-1991

TESTING CLIMATE ACCORDING TO ISO : 187 (50%h.r., 23°C)